



**1805TWSTB SLEEVE/ARMCOVER, WHITE,  
50 PAIRS/POLYBAG, 5 POLYBAGS  
PER POLYLINE CASE, STERILE**

**Description:**

GEPCO's Tyvek<sup>®</sup> Sleeves/Armcovers are made from DuPont Tyvek<sup>®</sup> fabric. This fabric offers exceptional fluid protection while allowing air and water vapor to pass through it for coolness and comfort. Tyvek<sup>®</sup> is abrasion and puncture resistant and is virtually lint-free. These Sleeves/Armcovers have an elastic upper and wrist. GEPCO's Tyvek<sup>®</sup> Sleeves/Armcovers are supplied sterile in Tyvek<sup>®</sup>/Mylar pouches. GEPCO's Tyvek<sup>®</sup> Sleeves/Armcovers are processed in a Class 1,000 clean room. The pouches are sterilized in lots using ethylene oxide gas sterilization. Each pouch includes a lot number for traceability.

**Specifications:** (Reorder No. 1805TWSTB)

PHYSICAL PROPERTIES		
Material – TYVEK <sup>®</sup> (Spunbonded Olefin) Type 1422A		
Basis Weight	1.2	oz. / sq. yd
Thickness	5.3	mils
Color	White	
Construction – Heat-sealed seam. Elastic upper. Elastic wrist. All elastic is latex-free.		
STRENGTH PROPERTIES – (MD signifies machine direction; CD signifies cross direction.)		
Strip Tensile (MD   CD)	7.9   7.6	lbs. / in.
Work to Break (MD   CD)	2.4   2.1	in.- lbs.
Tongue Tear (MD   CD)	2.2   2.4	lbs.
Mullen Burst	60	lbs. / sq. in.

**Sterilization Method:** Ethylene Oxide Gas (ETO) sterilization

**Packing:** 500 sleeves/armcovers (250pairs) per case. (2 sleeves/armcovers are packed in a Tyvek/Mylar pouch. 50 pouches are placed in a polybag, 5 polybags are placed in a polylined case.)

The information presented here is based on data which General Econopak believes to be reliable. It is presented to assist in product evaluation and verification. General Econopak makes no guarantee of results and assumes no obligation or liability connected with this information. Since conditions of use are outside our control, we make no warranties, express or implied, including without limitation, no warranties of fitness for a particular use and assume no liability in connection with any of this information. This data is subject to revision as technical knowledge and experience advances. Revisions are not intended to indicate a process or product change.