

**TECHNICAL SHEET**

# ABSO'NET SUPERIOR SPECIAL

Industrial absorption granules

**MINERALOGY<sup>1</sup>**

Calcined attapulgite

**PHYSICAL-CHEMICAL PROPERTIES**

	Typical Values <sup>1</sup>	Specifications <sup>2</sup>
Moisture (%) .....	2.7	< 5
Bulk density (g/l) .....	500	450 - 550
Water absorption <sup>3</sup> (%) .	150	> 135
Gasoil absorption <sup>3</sup> (%) .	150	> 135

**PARTICLE SIZE DISTRIBUTION  
DRY SIEVED**

SPECIFICATIONS <sup>2</sup>	ASTM	%
> 1.40 mm	> 14	< 3
0.60 – 1.40 mm	14 - 30	--
< 0.60 mm	< 30	< 3

<sup>1</sup> These data belong to an average analysis of our product.

<sup>2</sup> Applicable to the whole batch. Uncertainty of the method is not included.

<sup>3</sup> According to standard NF T 90-361